

SYNLAC INDUSTRIAL ENAMEL 5000 SERIES

PRODUCT CODE: SL 5000 Series

TECHNICAL DATA SHEET

Product Description	Premium quality, high gloss air drying industrial enamels.													
Intended Uses	<ul style="list-style-type: none"> • Ideal for earth moving equipment, tractors, transformers, trailers and truck bodies, buses. • May be overcoated by itself or other alkyd based coatings. 													
Features	<ul style="list-style-type: none"> • High gloss • Good exterior durability • Very good coverage 													
Product Information	Appearance Colours Tinting Generic type Solvent type Solids S G at 23°C Recommended DFT Theoretical spreading rate Supply viscosity at 23 °C Flash point	Gloss White(SL 5010), Black (SL 5050) and a range of tinted colours TINT BASE (SLB 5000) may be tinted on the Plascon Industrial Tinting system or manually to match virtually any solid colour using Plascon IAC colourants. Modified alkyd Aromatic and aliphatic hydrocarbon solvents Approx. 47 % by mass; 30 % by volume 1,01 kg/ℓ (typical) depending on colour Min.: 30 µm Max.: 50 µm 7,5 m ² /ℓ at 40 µm DFT 62 – 65 KU (typical) – varies with addition of colourants. 23°C												
Application Details	Mixing Method Thinner Cleaning Substrate Application Environment Drying time	Stir thoroughly with a flat paddle until homogeneous. Spray application. Can be brush applied unthinned on small areas. Thin to spray viscosity 16 – 20 seconds Ford Cup No. 4 at 23 °C with PLASCON FAST DRYING SOLVENT (PYY 1), ENAMEL THINNER (TH 77) or UNIVERSAL REDUCER (PUR 1) PLASCON FAST DRYING SOLVENT (PYY 1), ENAMEL THINNER (TH 77) UNIVERSAL REDUCER (PUR 1) or NO 40 LACQUER THINNER (ILS 1) Thoroughly cleaned and prepared surfaces.												
	Application Environment	<table border="1"> <thead> <tr> <th>Surface Temperature</th> <th>Ambient Temperature</th> <th>Relative Humidity</th> </tr> </thead> <tbody> <tr> <td>Min.: 10 °C</td> <td>Min.: 10 °C</td> <td>Min: 10%</td> </tr> <tr> <td colspan="3">or 2 °C min. above dew point</td> </tr> <tr> <td>Max.: 40 °C</td> <td>Max.: 35 °C</td> <td>Max.: 85 %</td> </tr> </tbody> </table>	Surface Temperature	Ambient Temperature	Relative Humidity	Min.: 10 °C	Min.: 10 °C	Min: 10%	or 2 °C min. above dew point			Max.: 40 °C	Max.: 35 °C	Max.: 85 %
Surface Temperature	Ambient Temperature	Relative Humidity												
Min.: 10 °C	Min.: 10 °C	Min: 10%												
or 2 °C min. above dew point														
Max.: 40 °C	Max.: 35 °C	Max.: 85 %												
	Drying time	Touch dry 30 Mins. at 23 °C Recoating 2 h at 23 °C Dry to handle 6 h at 23 °C												
Storage and Packaging	Store away from direct sun, heat and severe cold. Packaging: 1ℓ, 5ℓ, 25 ℓ and 200ℓ.													

SYNLAC INDUSTRIAL ENAMEL 5000 SERIES

PRODUCT CODE: SL 5000 Series

Surface Preparation	<p>All surfaces must be clean, dry and free from dust, dirt, oil, grease or any other contaminants.</p> <ul style="list-style-type: none"> Remove oil, grease and dirt and any other contaminants with PLASCON AQUASOLV DEGREASER (GR 1) Rinse thoroughly with clean water. <p>MILD STEEL:</p> <ul style="list-style-type: none"> Recommended Primers: COASTCOTE ETCH PRIMER (SNK 2), GP PRIMER RED OXIDE (WDD 28), QDP PRIMER SERIES ETCH PRIMER (SN 152) or COASTCOTE SERIES (SNK)
Application	<ul style="list-style-type: none"> Thin as recommended and apply to achieve the required DFT
Cautions	<ul style="list-style-type: none"> Bright clear transparent colours may require additional coats.
Safety Precautions	<ul style="list-style-type: none"> Always keep paint out of reach of children. Ensure good ventilation during application and drying. If accidental contact with skin should occur, wash immediately with soap and water or a recognised skin cleaner. Take care to avoid contact with the eyes. In case of contact, immediately rinse the eyes with plenty of water and seek medical attention. Harmful if swallowed. Seek medical attention and do not induce vomiting. Do not smoke while painting. Flammable. Store in a cool dry place away from heat and sparks. Refer to Material Safety Data Sheet for complete information.

DISCLAIMER:

The recommendations contained herein are given in good faith and are meant to guide the specifier or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

N.B. Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

N.B. TO ORDER: Quote product name, product code number, packaging and colour.

KANSAI PLASCON (PTY) LIMITED

CAPE TOWN:

P O Box 42
Eppindust 7475
Tel: (021) 505-2400
Fax: (021) 534-3791

DURBAN:

Private Bag X16
Mobeni 4060
Tel: (031) 451-3200
Fax: (031) 451-3411

GAUTENG:

P.O Box 4010
Luipaardsvlei 1743
Tel: (011) 951-4500
Fax: (011) 955-2841

PORT ELIZABETH:

P O Box 1594
Port Elizabeth 6000
Tel: (041) 401-1400
Fax: (041) 453-4606